



DESCRIPTION

41-30 PARAMOUNT Waterborne Wood Preservative is a waterborne ready to use for amateur and professional usage. It protects wood/timber against wood destroying fungi, blue stain fungi, termites and insects. Ideal for exterior wooden surfaces such as windows, exterior doors, claddings, eaves, fences, carports etc. Do not apply where the product during application can reach surface waters as e.g. a bridge over pond or direct soil contact or in marine environment. Type: Wood Preservative, Water Based. Active ingredient Regulation (EU) No 528/2012: 1) 3-iodo-2-propynyl butylcarbamate (55406-53-6) 0.75%, 2) propiconazole (ISO) (60207-90-1) 0.24%, 3) cypermethrin cis/trans +/-40/60; (RS)- α -cyano-3-phenoxybenzyl (1RS,3RS;1RS,3SR)-3-(2,2-dichlorovinyl)-2,2-dimethylcyclopropane carboxylate (52315-07-8) 0.15%

PERFORMANCE GUIDE

Weather Resistance	Excellent weather resistance.
Heat Resistance	Not applicable.
Water Resistance	Excellent rain and condensation resistance.
Abrasion Resistance	Not applicable.
Solvent Resistance	Not applicable.



product).

VOC (Volatile Organic Compounds): EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category A/h "Binding primers" Type WB): 30 g/L. This product contains maximum 29 g/L VOCs (ready for use

PERFORMANCE FEATURES

- Enhances the beauty of wood
- Protects wood against insects, fungi, mould, blue stains and every kind of micro-organisms.
- Deep penetration and elasticity.
- Allows wood to breath.
- Easy application, dries quickly.
- For Exterior use.




Colors:
Clear



Toxicity:
Formulated without lead or mercury.



Gloss Level: Flat 0-5



Spreading Rate

8-10 m²/L depending on wood porosity
Actual coverage may vary depending on substrate and application method

Volume Solids

15%+/- 1%

Wet Film Thickness

Minimum

Dry Film Thickness

Minimum

Dry Time at 20°C

30 minutes to touch
1-2 hours to recoat

Resin:

Acrylic Resin

Thinning

Do not thin

For Application By

Brush, Roller, Spray, Dipping

DIRECTION FOR USE

SURFACE PREPARATION

Surfaces must be clean, dry and free of dirt, oil or grease. Completely remove old or poorly adhering varnish and paint to expose new wood. Dry sanding, flame cutting and /or welding of the dry paint film will give rise to dust fumes. Wet sanding/flattening should be used wherever possible. • Ensure good ventilation during application and drying. Use suitable respiratory protective equipment. On tropical wood wash down with nitro thinner to remove resins that may lengthen dry times. If mildew is evident, it must be removed by scrubbing with a commercial mildew wash, following manufacturer's direction and cautions.

APPLICATION

Wood preservatives should be used cautiously. Please read product labels and directions before using the product. The product is ready-to-use and should not be diluted. Stir thoroughly prior to use. Close the container tightly after use. When applying, the wood moisture content shall not exceed 18% and the wood surface shall be dry, clean and free from decay at the time of treatment. During application and drying, the temperature should be above 5°C and the relative humidity should be below 80%. Cover the ground with a plastic sheet during outdoor application. Do not apply where the product during the application can reach surface waters as e.g., a bridge over pond.

Caution

Do not expose exterior wood only with a preservative or colorless.

Notice

Uneven color might show on film if applied when high humidity is present, which will disappear in time

CLEAN UP

Clean equipment in warm, soapy water.

PRECAUTIONS HEALTH, SAFETY AND ENVIRONMENTAL PROTECTION

Very toxic to aquatic life with long lasting effects. Safety data sheet available on request. If medical advice is needed, have product container or label at hand. Keep out of reach of children. Wear protective gloves/protective clothing/eye protection/face protection. Avoid release to the environment. Collect spillage. Dispose of contents and container in accordance with all local, regional, national and international regulations. Contains propiconazole (ISO) and 3-iodo-2-propynyl butylcarbamate. May produce an allergic reaction. 5% of the mixture consists of component(s) of unknown toxicity. Contains 5% of components with unknown hazards to the aquatic environment. Keep container tightly closed.

FIRST AID MEASURES:

Get medical attention immediately. If inhaled, remove to fresh air. If not breathing, if breathing is irregular or if respiratory arrest occurs, provide artificial respiration or oxygen by trained personnel. Do not induce vomiting unless directed to do so by medical personnel. Never give anything by mouth to an unconscious person. Additional information: See Section 4 of the safety data sheet (first aid measures).

License number: TP8-0120 (Troy Chemical Europe B.V. - Uiverlaan 12e - 3145 XN Maassluis - The Netherlands - Tel: +31-10-5927494 - Emergency Tel: +1 703-741-5970)

Packaging and Storage

Sizes: 0,75 litres, 2,25 litres

Flash Point: none

Storage: Refer to Safety Data Sheet

For Advising – Technical Services call: 2106620713-5

